

COLD POUR CRACK SEALANT – VISCOSITY (STORMER)

1.0 SCOPE

- 1.1 This test method describes the procedures for determining the consistency of rubberized asphalt emulsion crack sealant using the Stormer Viscometer.

2.0 APPLICABLE DOCUMENTS

- 2.1 ASTM D562 Standard Test Method for Consistency of Paints using the Stormer Viscometer

3.0 APPARATUS AND PROCEDURES

- 3.1 The equipment and procedures used are as per those in the above mentioned publication with the following modifications:

- 3.1.1 Stormer Viscometer with Stroboscopic timer
- 3.1.2 Water bath maintained at $25 \pm 1^{\circ}\text{C}$
- 3.1.3 Thermometer ASTM 17F 19 - 30°C , 0.1°C divisions or equivalent

4.0 REPORT

- 4.1 The calculated Krebs Units (KU).